

SVA is a closed cell, cross-linked expanded Ethylene Vinyl Acetate foam available in various densities, which is suitable for use in packaging, padding, buoyancy, gasketing and footwear components. The SVA product range is free from CFC's and HCFC's.

PROPERTY	UNIT	TEST METHOD	NOMINAL ⁽¹⁾	RANGE
DENSITY:	kg / m ³	ISO 845	33	29 - 41 ⁽²⁾
TENSILE STRENGTH:				
CD	kPa	ISO 1798	329	>262
MD	kPa	ISO 1798	329	>267
ELONGATION:				
CD	%	ISO 1798	405	>330
MD	%	ISO 1798	371	>291
COMPRESSION DEFLECTION:				
10 %	kPa	ISO 3386 / 1	18	12 - 24
25 %	kPa	ISO 3386 / 1	33	26 - 41
50 %	kPa	ISO 3386 / 1	80	68 - 93
COMPRESSION-SET:				
25 % 22 hr COMP / 30 min REC	%	ISO 1856	21	26
25 % 22 hr COMP / 24 hr REC	%	ISO 1856	14	23
50 % 22 hr COMP / 30 min REC	%	ISO 1856	39	51
50 % 22 hr COMP / 24 hr REC	%	ISO 1856	32	47
MAXIMUM OPERATING TEMPERATURE: ⁽³⁾	°C	INTERNAL	50	N/A
BURN RATE: ⁽⁴⁾	mm / min	INTERNAL	61	<100
BURN RATE:	mm / sec	ISO 3582	1.3	<-5
SHORE HARDNESS:	OO	INTERNAL	41	33 - 49
THERMAL CONDUCTIVITY:				
10 mm	W / m.K	ASTM C-518	0.036	N/A
20 mm	W / m.K	ASTM C-518	0.036	N/A
WATER ABSORPTION:	%	ASTM D 570-98	<1	<1

- NOMINAL:**
Indicative average value.
- DENSITY:**
Based on 90 % net bun yield.
- MAXIMUM OPERATING TEMPERATURE:**
Defined as the temperature which will typically cause an average linear shrinkage of no more than 2 % after a 1 hour exposure period. The percentage shrinkage of a sample, having the dimensions 100mm by 100mm by 10mm, with respect to its length, width and thicknesses is used to calculate the average linear shrinkage. The degree of shrinkage depends on the material type, density, temperature, exposure time, part dimensions and cell size. Other temperatures may prove to be limiting depending on the particular conditions of each application. The above quoted value will be deemed not applicable, if any deviation from the above mentioned sample dimensions are to occur.
- BURN RATE:**
A 10mm thick sample is used to determine the horizontal burn rate of the relevant material. The above quoted value will be deemed not applicable, if any deviation from the above mentioned sample dimensions are to occur. Test based on FMVSS302.
- BURN RATE:**
A 13mm thick sample is used to determine the horizontal burn rate of the relevant material. The above quoted value will be deemed not applicable, if any deviation from the above mentioned sample dimensions are to occur.

PLEASE NOTE:

The above results are obtained based on the referenced test methods and are to be regarded as typical values which are not usually directly comparable with those of any product tested to other test methods, i.e.: DIN. Tests were conducted at ambient temperature and humidity unless otherwise stated.

Whilst this document has been prepared in good faith, Sondor Industries (Pty) Ltd accept no contractual liability of any kind to any person in respect of its contents or any use made thereof, nor must it be assumed that any such use will not infringe any patent. This document shall form no part of any contract with a customer. The data supplied on this sheet is typical and in no way reflects the final resultant values of the respective products.

sondor
PERFORMANCE FOAMS



CAPE TOWN: Tel: (021) 959 9400, E-mail: SondorCPT@sondor.co.za · **DURBAN:** Tel: (031) 705 4220, E-mail: SondorDBN@sondor.co.za
JOHANNESBURG: Tel: (011) 452 4530, E-mail: SondorJHB@sondor.co.za · **PORT ELIZABETH:** Tel: (041) 486 2231, E-mail: SondorPE@sondor.co.za
PRETORIA: Tel: (012) 803 4471, E-mail: SondorPTA@sondor.co.za · **EXPORTS:** Tel: +27-21-959 5900, E-mail: SondorEXPORTS@sondor.co.za
HEAD OFFICE: Tel: (021) 959 5900, E-mail: SondorHO@sondor.co.za · **EAST LONDON AGENT:** Johnny Grant (043) 743 3067/68
GARDEN ROUTE AGENT: IMPI Wire (044) 802 7300